



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

FINELINER INKS - EXTRAFINE

TECHNICAL CHARACTERISTICS

Fineliner are water-based inks for filter system.
The dye-based formula shows good flowing properties and it's suitable with all kinds of paper.

Wide range of colors from catalogue and on requirement.

Colour Ref. No:	pH	Viscosity (SC4-18; 200 rpm)	Surface Tension	Specific Gravity
Black 672	4,92 ± 1	2,49 ± 1	36,19 ± 2	1,0300 ± 0,15
Red 670	4,40 ± 1	2,01 ± 1	32,86 ± 2	1,0450 ± 0,15
Red 2662	4,40 ± 1	2,01 ± 1	32,90 ± 2	1,0450 ± 0,15
Red 4097	4,40 ± 1	2,01 ± 1	32,90 ± 2	1,0450 ± 0,15
Blue 645/2	4,91 ± 1	2,38 ± 1	38,10 ± 2	1,0500 ± 0,15
Blue 2660	5,00 ± 1	2,40 ± 1	38,00 ± 2	1,0500 ± 0,15
Green 563	3,96 ± 1	1,93 ± 1	35,71 ± 2	1,0520 ± 0,15
Yellow 2614	4,06 ± 1	1,90 ± 1	32,38 ± 2	1,0370 ± 0,15
Pink 1766	10,00 ± 1	1,83 ± 1	36,19 ± 2	1,0430 ± 0,15
Brown 1766	4,50 ± 1	2,17 ± 1	35,24 ± 2	1,0512 ± 0,15
Turquoise 1841	4,50 ± 1	1,81 ± 1	37,62 ± 2	1,0230 ± 0,15
Orange 1841	8,70 ± 1	1,90 ± 1	34,52 ± 2	1,0508 ± 0,15
Light Grey 1841	7,22 ± 1	1,59 ± 1	35,48 ± 2	1,0420 ± 0,15
Ochre 1841	5,45 ± 1	1,87 ± 1	37,14 ± 2	1,0440 ± 0,15
Blue-Green 1859	5,04 ± 1	1,77 ± 1	38,10 ± 2	1,0490 ± 0,15
Light Lilac 1859	4,14 ± 1	1,60 ± 1	35,00 ± 2	1,0200 ± 0,15
Bordeaux 1814	4,31 ± 1	1,83 ± 1	34,76 ± 2	1,0275 ± 0,15
Magenta 1841	3,20 ± 1	2,10 ± 1	34,29 ± 2	1,0460 ± 0,15
Olive green 1859	5,80 ± 1	1,87 ± 1	33,81 ± 2	1,0336 ± 0,15
Light Blue 908	3,75 ± 1	1,69 ± 1	33,81 ± 2	1,0227 ± 0,15
Medium Grey 2388	5,40 ± 1	1,83 ± 1	34,29 ± 2	1,0250 ± 0,15
Dark Grey 2389	4,05 ± 1	1,86 ± 1	34,29 ± 2	1,0380 ± 0,15
Light Grey 2387	4,87 ± 1	1,78 ± 1	34,29 ± 2	1,0286 ± 0,15
Light Green 1766	8,12 ± 1	1,98 ± 1	34,29 ± 2	1,0373 ± 0,15
Light Blue 1841	5,03 ± 1	1,42 ± 1	34,29 ± 2	1,0112 ± 0,15
Light Turquoise 1766	4,70 ± 1	1,54 ± 1	37,62 ± 2	1,0180 ± 0,15
Dark Green 1841	5,04 ± 1	2,35 ± 1	38,10 ± 2	1,0580 ± 0,15
Blush 2488 - 196U	4,40 ± 1	1,59 ± 1	37,14 ± 2	1,0200 ± 0,15
Blue 908	3,81 ± 1	2,05 ± 1	34,52 ± 2	1,0419 ± 0,15
Dark Turquoise 2630	3,55 ± 1	2,11 ± 1	33,33 ± 2	1,0370 ± 0,15
Jade 2865	4,88 ± 1	1,83 ± 1	47,14 ± 2	1,0410 ± 0,15
Dark Green New 2866	4,11 ± 1	1,81 ± 1	32,62 ± 2	1,0390 ± 0,15
Purple New 3242	8,00 ± 1	2,10 ± 1	35,00 ± 2	1,0500 ± 0,15

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

SUITABLE COMPONENTS

Nibs/Tips: Polyester with Stainless Steel Adapter

Reservoir: Polyester

Body: Polypropylene

Cap: Polypropylene, Polyethylene

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store frost protected. Optimal storage temperature is between 15°C and 30°C. Storage temperatures above 35°C can result in reduced shelf life of the inks.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums

200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.