



Strada del Francese, 21
 10071 Borgaro Torinese – Torino – ITALY
 Ph.: +39 (011) 4701510 or 4701511 or 4704541
 Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

HIGH OPACITY FIBER PEN INKS 4026

TECHNICAL CHARACTERISTICS

High opaqueness 4026 are pigmented water-based inks formulated for filter system markers. They bring high-covering power into reservoir markers. Can write well

on all kind of non-porous surfaces (glass, PP-foils, whiteboards, blackboards). They show good adhesion but can yet be easily removed with a wet cloth or water. Very good lightfastness.

Colour ref. No:	WHITE 4026	LIGHT GREEN 4026	ORANGE 4026	YELLOW 4026
Viscosity Brookfield LV2 200rpm (cps, 25 °C) range:	50 - 60	50 - 60	50 - 60	50 - 60
pH :	10 ± 1	10 ± 1	9 ± 1	9 ± 1
Colour ref. No:	SKY-BLUE 4026	BLACK 4026		
Viscosity Brookfield LV2 200rpm (cps, 25 °C) range:	50 - 60	50 - 60		
pH :	10 ± 1	10 ± 1		

SUITABLE COMPONENTS

Markers should ideally be stored horizontally and should be capped firmly.

Nibs/Tips: Porosity 65-68% (like Aubex JH455F or similar)

Reservoirs: Density 0,155-0,170 g/cm3 (like De Martini CPES3475, CPES3496 or similar)

Body: HDPE, Polypropylene

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct

sunlight. Cleaning of all filling devices should be done immediately after finishing the process.

INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums
 200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.