



Strada del Francese, 21
 10071 Borgaro Torinese – Torino – ITALY
 Ph.: +39 (011) 4701510 or 4701511 or 4704541
 Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

ACRI WOOD INKS 4096

TECHNICAL CHARACTERISTICS

Acri wood inks 4096 are permanent water-based ink for valve system. Opaque lacquer-finish ink ideal for touching up and sealing of scratches on solid woods.

Waterproof, smudge-proof, quick-drying, low-odour and resistant against most mild common household detergents.

Colour ref. No:	BEECH 4096	CHERRY 4096	MAHOGANY 4096	LIGHT OAK 4096	WALNUT 4096
Viscosity, cps (25 °C) Brookfield LV1 100rpm	30 ± 5	30 ± 10	30 ± 10	30 ± 10	30 ± 10
pH :	8 ± 1	8 ± 1	8 ± 1	8 ± 1	8 ± 1
Light Fastness (Blue Woodscale)	8	8	8	8	8

SUITABLE COMPONENTS

Use valve action markers only. Markers should ideally be stored horizontally and should be capped firmly.

Nibs/Tips: High-porosity polyester nibs suitable for pigments (porosity 60-65%)

Inner Ball: Corrosion safe ball, both stainless steel or glass

Body: HDPE , Polypropylene

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct

sunlight. Cleaning of all filling devices should be done immediately after finishing the process.

INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums
 200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.