



Strada del Francese, 21
 10071 Borgaro Torinese – Torino – ITALY
 Ph.: +39 (011) 4701510 or 4701511 or 4704541
 Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

WINDOW FIBER PEN INKS 2129

TECHNICAL CHARACTERISTICS

Window 2129 are water-based inks formulated for filter system markers.
 Translucent yet bright and glossy colors specially developed to write

on glass. Excellent lightfastness. The inks can easily be removed with a wet cloth or water.

Wide range of colors from catalogue and on requirement.

Colour ref. No:	GREEN 2129	BLACK 2129	BLUE 2129	RED 2129
Viscosity (Brookfield SC4-18 200rpm, cps at 25°C)	7 - 9	7 - 9	7 - 9	7 - 9
pH :	6 - 8	6 - 8	6 - 8	6 - 8
Light Fastness (Xenon test for 20hrs)	Excellent, no alterations	Excellent, no alterations	Excellent, no alterations	Excellent, no alterations
Colour ref. No:	YELLOW 2129	BROWN 2129	BLACK 2722	
Viscosity (Brookfield SC4-18 200rpm, cps at 25°C)	7 - 9	7 - 9	7 - 9	
pH :	6 - 8	6 - 8	6 - 8	
Light Fastness (Xenon test for 20hrs)	Excellent, no alterations	Excellent, no alterations	Excellent, no alterations	

SUITABLE COMPONENTS

Nibs/Tips: Nylon, Polyester
Reservoir: Polyester (density 0,140-0,160 g/cm3)
Body: Polypropylene
Cap: Polypropylene, Polyethylene
 It is recommended to thoroughly test the components selected.

and 30°C. Storage temperatures above 35°C can result in reduced shelf life of the inks.

Cleaning of all filling devices should be done immediately after finishing the process.

Drums should be closed tightly during storage.

HANDLING INSTRUCTIONS

Store frost protected. Optimal storage temperature is between 15°C

PACKING

50 KG net Plastic Drums
 200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.