



Strada del Francese, 21  
 10071 Borgaro Torinese – Torino – ITALY  
 Ph.: +39 (011) 4701510 or 4701511 or 4704541  
 Fax +39 (011) 4703910 – Email: [info@reinol.it](mailto:info@reinol.it)

## TECHNICAL DATA SHEET

### ACRI METAL INKS 2733

#### TECHNICAL CHARACTERISTICS

Acri 2733 are pigmented water-based metal inks formulated for valve action markers.  
 They can write smoothly on all kind of surfaces, both porous and non-

porous.  
 Excellent colored metal effect on black paper.  
 Wide range of colors from catalogue and on requirement.

Colour ref. No:	METAL SILVER 2733	METAL GOLD 2733	METAL BLUE 2733	METAL RED 2733	METAL BRONZE 2733
Viscosity, cps (25 °C) Brookfield LV1 100rpm	15 ± 5	15 ± 5	15 ± 5	15 ± 5	15 ± 5
pH :	8 ± 1	8 ± 1	8 ± 1	8 ± 1	8 ± 1
Light Fastness (Blue Woodscale)	8	8	8	8	8
Colour ref. No:	METAL PINK 2733	METAL VIOLET 2733	METAL GREEN 2733	METAL TURQUOISE 2733	
Viscosity, cps (25 °C) Brookfield LV1 100rpm	15 ± 5	15 ± 5	15 ± 5	15 ± 5	
pH :	8 ± 1	8 ± 1	8 ± 1	8 ± 1	
Light Fastness (Blue Woodscale)	8	8	8	8	

#### SUITABLE COMPONENTS

Use valve action markers only. Markers should ideally be stored horizontally and should be capped firmly.

**Nibs/Tips:** High-porosity polyester nibs suitable for pigments (porosity 60-65%)

**Inner Ball:** Corrosion safe ball, both stainless steel or glass

**Body:** HDPE , Polypropylene

It is recommended to thoroughly test the components selected.

#### HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct

sunlight. Cleaning of all filling devices should be done immediately after finishing the process.

#### INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

#### PACKING

50 KG net Plastic Drums  
 200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.