



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

Changing Color VARIACOLOR F/P INKS (meeting EU toy requirements)

TECHNICAL CHARACTERISTICS

Variacolor are dye / water-based inks for filter system markers.
The different shades are color changing using the Revealer 972-00.
They are suitable for all kind of papers. Note that chemical

characteristics of the used paper may lead to a slight color change after some days.

Colour ref. No:	ORANGE / YELLOW 4045	BLUE / FLIO YELLOW 972/04 (2964)	BROWN / LIGHT GREEN 972/18 (2964)	BLUE / SKY-BLUE 972/05 (2964)	GREEN / CARROT 2324 (2964)	YELLOW / RED 972/13 (2964)
Viscosity (Brookfield SC4-18 200rpm, cps at 25°C)	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1
pH:	4 ± 1	4 ± 1	4 ± 1	4 ± 1	4 ± 1	4 ± 1
Unit Weight (at 25°C)	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15
Colour ref. No:	BLUE VIOLET / LIGHT GREEN 1871	RED / YELLOW 2817 (2964)	DARK GREEN / YELLOW 972/09	PINK / YELLOW 4045	REVEALER 972-00 (2964)	
Viscosity BROOKFIELD LV1, rpm 200 (cps, 25°C)	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	
pH:	4 ± 1	4 ± 1	4 ± 1	4 ± 1	10,5 ± 1	
Unit Weight (at 25°C)	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15	1,025 ± 0,15	1,050 ± 0,05	

SUITABLE COMPONENTS

Nibs/Tips: Polyester
*Nylon nibs are not recommended due to possible color changes
Reservoir: Polyester
Body: Polypropylene, Polyethylene
Cap: Polypropylene, Polyethylene
It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store frost protected. Optimal storage temperature is between 15°C and 30°C. Storage temperatures above 35°C can result in reduced shelf life of the inks.
Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums
200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.