



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

PAINT MARKER INKS 2568

TECHNICAL CHARACTERISTICS

Paint inks 2568 are pigmented inks formulated with organic, inorganic and metallic pigments for valve action markers. They can write smoothly on all kind of surfaces. Great covering, lightfastness and water-resistance.

Maximum adhesion on any surface
Free from aromatic/chlorinated solvents.

Colour ref. No:	BLACK 2568	WHITE 2568	BLUE 2568	RED 2568	YELLOW 2568
Viscosity, cps (25 °C) Brookfield LV1 100rpm	8 ÷ 12	8 ÷ 12	8 ÷ 12	8 ÷ 12	8 ÷ 12
Lightfastness (1-8)	8	8	8	6/7	7
Unit Weight (g/cm3)	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12
Colour ref. No:	GREEN 2568	FLUO YELLOW 2568	GOLD 2568	SILVER 2568	COPPER 2568
Viscosity, cps (25 °C) Brookfield LV1 100rpm	8 ÷ 12	8 ÷ 12	8 ÷ 12	8 ÷ 12	8 ÷ 12
Lightfastness (1-8)	7/8	5	8	8	8
Unit Weight (g/cm3)	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12	0,95 ÷ 1,12

SUITABLE COMPONENTS

Use valve action markers only. Markers should ideally be stored horizontally and should be capped firmly.

Nibs/Tips: High-porosity polyester nibs suitable for pigments and solvent-resistant, porosity 60-65%

Inner Ball: Corrosion safe ball, both stainless steel or glass

Body: Aluminium

Cap, Front Section: PBT, nylon

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct sunlight.

CAUTION: the inks are flammable liquids! Keep away from heat, hot surfaces, sparks, open flames and other ignition sources.

After use clean the filling unit with alcohol or MEK.

INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic or Metal Drums

200 KG net Plastic or Metal Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.