



Strada del Francese, 21  
10071 Borgaro Torinese – Torino – ITALY  
Ph.: +39 (011) 4701510 or 4701511 or 4704541  
Fax +39 (011) 4703910 – Email: [info@reinol.it](mailto:info@reinol.it)

## TECHNICAL DATA SHEET

### TEXTILE FLUO INKS 2955

#### TECHNICAL CHARACTERISTICS

Textile 2955 are pigmented fluo water-based inks formulated for filter system.  
They are suitable for any kind of fabric. The applied ink should dry on

the fabric for at least one day before becoming permanent (even without ironing).

Wide range of colors from catalogue and on requirement.

Colour ref. No:	FLUO PINK 2955	FLUO ORANGE 2955	FLUO YELLOW 2955	FLUO SKY-BLUE 2955	FLUO GREEN 2955	FLUO VIOLET 2955
Viscosity BROOKFIELD Small Sample Adapter, Spindle SC4-18, rpm 100 (cps, 25°C)	< 20	< 20	< 20	< 20	< 20	< 20
Ph	8 ± 1	8 ± 1	8 ± 1	8 ± 1	8 ± 1	8 ± 1
Surface Tension (mN/m)	40 ± 3	40 ± 3	40 ± 3	40 ± 3	40 ± 3	40 ± 3

#### SUITABLE COMPONENTS

Markers should ideally be stored horizontally and should be capped firmly.

**Nibs/Tips:** Polyester (porosity over 60%)

**Reservoir:** Polyester

**Body:** Polypropylene, Polyethylene

**Cap:** Polypropylene, Polyethylene

It is recommended to thoroughly test the components selected.

#### HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct

sunlight. Storage temperatures above 35°C can result in reduced shelf life of the inks. After use clean the filling unit.

#### INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

#### PACKING

50 KG net Plastic Drums  
200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.