



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

ERASABLE WRITE - OVERWRITE INKS

TECHNICAL CHARACTERISTICS

The Erasable inks can be totally erased using Reinol Erasing Liquid 555.

While the overwrite ink can write on the erased part without changing its color. They are suitable for all kind of papers.

Note that chemical characteristics of the used paper may lead to a slight color change after some days.

Colour ref. No:	LIGHT BLUE 1575	BLUE 942/05	PERWINKLE 942/13	CYCLAMEN 942/17	LILAC 2912	PINK 2634	DARK GREEN 2823	LIGHT GREEN 2812
Action:	write / erasable	write / erasable	write / erasable	write / erasable	write / erasable	write / erasable	write / erasable	write / erasable
Viscosity (cps at 20°C)	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1
pH:	4 ± 0,5	3 ± 0,5	4 ± 0,5	4 ± 0,5	4 ± 0,5	3 ± 0,5	4 ± 0,5	3 ± 0,5
Surface tension (dyne/cm ²)	48 ± 5	48 ± 5	48 ± 5	48 ± 5	48 ± 5	48 ± 5	48 ± 5	48 ± 5
Colour ref. No:	INDIGO 2826	RED 2911	FLUO YELLOW 1165	FLUO GREEN 1165	SKY-BLUE 1165	LILAC 1165	PINK 1165	REVEALER 555
Action:	write / erasable	write / erasable	overwrite	overwrite	overwrite	overwrite	overwrite	erase
Viscosity (cps at 20°C)	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1	2,5 ± 1
pH:	4 ± 0,5	4 ± 0,5	11 ± 0,5	11 ± 0,5	11 ± 0,5	11 ± 0,5	11 ± 0,5	11 ± 0,5
Surface tension (dyne/cm ²)	48 ± 5	48 ± 5	42 ± 5	42 ± 5	42 ± 5	42 ± 5	42 ± 5	42 ± 5

SUITABLE COMPONENTS

Nibs/Tips: Polyester

*Nylon nibs are not recommended due to possible color changes

Reservoir: Polyester

Body: Polypropylene, Polyethylene

Cap: Polypropylene, Polyethylene

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store frost protected. Optimal storage temperature is between 15°C and 30°C. Storage temperatures above 35°C can result in reduced shelf life of the inks.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums

200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.