



Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

CHALK FLUO INKS 3229

TECHNICAL CHARACTERISTICS

Chalk 3229 are pigmented water-based inks formulated for valve action markers.

Brilliant fluo colors with high covering power that can write on all

kind of non-porous surfaces (glass, PP-foils, whiteboards, blackboards). The inks can easily be removed with a wet cloth or water.

Colour ref. No:	WHITE 3229	FLUO GREEN 3229	FLUO ORANGE 3229	FLUO RED 3229
Viscosity, cps (25 °C) Brookfield LV2 200rpm	35 ± 5	20 ± 5	20 ± 5	20 ± 5
pH :	8 ± 1	8 ± 1	8 ± 1	8 ± 1
Colour ref. No:	FLUO PINK 3229	FLUO YELLOW 3229	FLUO PURPLE 3229	
Viscosity, cps (25 °C) Brookfield LV2 200rpm	20 ± 5	20 ± 5	20 ± 5	
pH :	8 ± 1	8 ± 1	8 ± 1	

SUITABLE COMPONENTS

Use valve action markers only. Markers should ideally be stored horizontally and should be capped firmly.

Nibs/Tips: High-porosity polyester nibs suitable for pigments (porosity 60-65%)

Inner Ball: Corrosion safe ball, both stainless steel or glass

Body: HDPE , Polypropylene

It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store between 15°C and 35°C. Do not expose loose ink to temperatures higher than 35°C. Protect from frost and avoid direct

sunlight. Cleaning of all filling devices should be done immediately after finishing the process.

INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.

Drums should be closed tightly during storage.

PACKING

50 KG net Plastic Drums

200 KG net Plastic Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.