Strada del Francese, 21
10071 Borgaro Torinese – Torino – ITALY
Ph.: +39 (011) 4701510 or 4701511 or 4704541
Fax +39 (011) 4703910 – Email: info@reinol.it

TECHNICAL DATA SHEET

WHITEBOARD MARKER INKS – FLUO 4067

TECHNICAL CHARACTERISTICS

Whiteboard are pigmented water-based inks. They come in bright and fluorescent colors, allowing for smooth writing on all whiteboards. Once dried, the markings can be easily erased with a wet cloth.

Colour ref. No:	FLUO YELLOW 4067	FLUO ORANGE 4067	FLUO PINK 4067	FLUO VIOLET 4067	FLUO VIOLET 4396
Viscosity, cps (25 °C) Brookfield LV1 100rpm	< 15	< 15	< 15	< 15	< 15
Unit Weight	1,045 ± 0,07	1,045 ± 0,07	1,045 ± 0,07	1,045 ± 0,07	1,045 ± 0,07
Ph:	7,5 ± 1	7,5 ± 1	7,5 ± 1	7,5 ± 1	7,5 ± 1

SUITABLE COMPONENTS

Markers should ideally be stored horizontally and should be capped firmly. Do not keep markers tip upwards.
Nibs/Tips: Polyester for alcohol-based inks (porosity ~68%)
Reservoir: Polyester for alcohol-based inks (density 0,140-0,160 g/cm3)
Body: Polypropylene, Polyethylene
Cap, Polypropylene, Polyethylene
It is recommended to thoroughly test the components selected.

HANDLING INSTRUCTIONS

Store between 15°C and 30°C. Do not expose loose ink to temperatures higher than 30°C. Protect from frost and avoid direct sunlight.

CAUTION: the inks are flammable liquids! Keep away from heat, hot surfaces, sparks, open flames and other ignition sources.
After use clean the filling unit with alcohol or MEK.

INSTRUCTION FOR USE

Stir ink in the drums well before use for at least 15-20 min. Keep the inks under stirring while filling markers in order to avoid pigment sedimentation.
Drums should be closed tightly during storage.

PACKING

50 KG net Plastic or Metal Drums
200 KG net Plastic or Metal Drums

Any and all statements, information and recommendations contained in the present technical sheet are drawn up to the best of the experience and knowledge of Reinol and based on tests which we regard as reliable. Nevertheless this does not imply any responsibility, either implicit or explicit, on the side of Reinol. Buyers shall bear all risks arising from the use of the products, it is therefore understood that the sale of the product is not protected by any guarantee, either implicit or explicit.